



MOLYKOTE® 1000 Paste

Solid lubricant paste for bolted metal joints; contains no lead or nickel

Features & benefits

- Can be used over a wide range of temperatures (-30°C/-22°F to +650°C/1,202°F)
- High load-carrying capacity
- Enables nondestructive dismantling, even after long use at high temperatures
- Coefficient of friction unchanged in the area of oiled bolts, even after several bolt retightening and loosening processes
- Good corrosion protection

Composition

- Solid lubricants
- Mineral oil
- Thickener
- Powdered metal

Applications

Suitable for bolted joints that are subjected to high temperatures up to 650°C (1,202°F) and to corrosive effects – and that after assembling and the initial operation, have to be retightened or disconnected. In order to ensure constant pre-stressing forces, uniform and steady coefficients of friction of the lubricant are necessary. Used successfully for cylinder head bolts, nozzle head screws of plastic injection molding machines, bolted joints in the chemical industry, and also for the tension rings of centrifuges.

Description

MOLYKOTE® 1000 Paste is a lead- and nickel-free anti-seize paste used to reduce wear and optimize friction of threaded fasteners, or other metal-to-metal joints, enabling nondestructive dismantling, even after long exposure to high temperatures. It offers good corrosion protection, under high loads, over a wide temperature range.

How to use

If possible, clean the thread and the bolt with a wire brush. Spread an adequate amount of the paste on the thread, right up to its root to obtain a good seal. In order not to alter the properties, the paste must not be mixed with grease or oils.

To enable this product to be applied more quickly and cleanly to larger areas, it is advisable to use the spray can.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

| Standard ⁽¹⁾ | Test | Unit | Result |
|--|--|----------|----------------------------|
| | Color | | Brown |
| Penetration, density | | | |
| ISO 2137 | Unworked penetration | mm/10 | 280-310 |
| ISO 2811 | Density at 20°C (68°F) | g/ml | 1.26 |
| Temperature | | | |
| | Service temperature range ⁽²⁾ | °C °F | -30 to 650 -22 to 1,202 |
| Load-carrying capacity, wear protection, service life | | | |
| | Four-ball tester | | |
| DIN 51 350 pt.4 | Weld load | N | 4,800 |
| DIN 51 350 pt.5 | Wear scar under 400 N load | mm | 0.65 |
| | Almen-Wieland machine | | |
| | OK load | N | 20,000 |
| | Frictional force | N | 2,600 |
| Coefficient of friction | | | |
| | Screw test - μ thread ⁽³⁾ | | 0.13 |
| | Screw test - μ head | | 0.08 |
| | Initial break-away torque ⁽⁴⁾ | Nm | 135 |
| DIN 51 802 | SKF-Emcors method | | 1 |

⁽¹⁾ISO: International Standardization Organization. DIN: Deutsche Industrie Norm.

⁽²⁾Temperature resistance of solid lubricants.

⁽³⁾Coefficient of friction in bolted connection, M12, 8.8, on blackened surface.

⁽⁴⁾M 12, with starting torque $M_a = 62$ Nm and heat treatment at 540°C (1,004°F), 21 hr, bolt material: no. 1.7709.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored at or below 20°C (68°F) in the original unopened containers, MOLYKOTE® 1000 Paste has a usable life of 60 months from the date of production.

Specifically for aerosol packaging, this product has a usable life of 24 months from the date of production when stored between 5°C and 35°C in the original unopened container. Because it is an aerosol, punctures should be avoided, and containers should be kept away from heat, sparks and open flame.

Packaging

This product is available in different standard container sizes as shown on molykote.com. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 1997-2022 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.