



**PLANARCORE® PVA BRUSHES WITH
MOLDED POLYPROPYLENE CORE**

*Rapid changeout and high performance for
the most critical post CMP clean applications*



rapid changeout and high performance

Overview

Planarcore® PVA brushes with molded polypropylene (PP) disposable cores are designed to deliver superior performance and wafer-to-wafer uniformity in post CMP wafer cleaning applications. The unique molded-through-the-core technology provides absolute adhesion of the PVA (polyvinyl alcohol) to the polypropylene brush core, unlike standard PVA products that are merely friction fitted to the core. The dimensional stability of disposable Planarcore PVA brushes also eliminates the uncertainty associated with stand-alone and pre-mounted PVA products. PVA slippage, expansion and loss of concentricity are no longer a concern with the superior performance of Planarcore PVA brushes from Entegris.

Reduces Downtime on Tool

Molded-through-the-core technology guarantees a perfect fit every time. No operator errors or

inconsistencies to worry about. Gapping is quicker and easier, as the dimensional stability and concentricity from brush to brush do not waver. From first wafer to last wafer, the Planarcore brush and gap remain the same, ensuring process stability.

Efficient cleaning processes in Planarcore brush manufacturing reduce fab-based flush-up and brush break-in times. Quicker CMP tool startup benefits throughput.

Decreases Defectivity on Wafer

Reduced particle counts on wafer are the result of cleaner PVA, dimensional consistency and flow equalization, which combine to deliver the most consistent performance wafer to wafer in the industry.

Features	Benefits
Molded-through-the-core construction	<p>Allows rapid and consistent installation on tools, reducing system downtime</p> <p>Eliminates alignment and gapping problems, increasing system throughput</p> <p>PVA remains dimensionally stable due to the molded-through-the-core technology; will not lose concentricity during use</p>
High-purity PVA	<p>Molded-through-the-core construction allows for more efficient cleaning of PVA in manufacture</p> <p>Brush break-in and flush-up time is dramatically reduced</p> <p>Low extractables and reduced particle counts on wafers</p>
Close molded technology	<p>The Planarcore brush design equilibrates flow through the brush, eliminating the risk of non-repeatable and non-predictable performance due to inconsistent flow rates through the length of the brush, as seen in standard designs</p>

Specifications

Materials of construction:	Core/mandrel	All-polypropylene construction	
	Brush	Polyvinyl alcohol (PVA)	
	Preservative	0.5% H ₂ O ₂ or NH ₄ OH	
Product cleanliness:*	Fluoride	F ⁻	<0.50 ppm (parts-per-million)
	Chloride	Cl ⁻	<0.75 ppm
	Nitrate	NO ₃ ⁻	<0.50 ppm
	Phosphate	PO ₄ ³⁻	<0.50 ppm
	Sulfate	SO ₄ ²⁻	<0.50 ppm
	Lithium	Li ⁺	<0.10 ppm
	Sodium	Na ⁺	<0.50 ppm
	Potassium	K ⁺	<0.80 ppm
	Magnesium	Mg ²⁺	<0.20 ppm
	Calcium	Ca ²⁺	<0.50 ppm
Dimensions:	Outside diameter**	70 mm ±1.0 mm	
	Concentricity**	<0.76 mm (0.03")	
PVA typical characteristics:	30% compressive stress**	90 g/cm ²	
	Porosity***	87–91%	
	DI water absorption capacity	700–1100 wt %	
	Pore size	70–250 μm (via SEM)	


*Full Planarcore brush (including core) is submerged in 1 L of 18 MΩ DI water and squeezed to ensure good distribution of any potential contamination. Residual DI water is then extracted by ion chromatography.

**These parameters are specified on the Certificate of Analysis for each product.


***Typical porosity is reported for the nodule area.

Dimensions

VVP1ARXR1 and PVPOARXR1 Planarcore Brush



VVP1AMMR1 and PVPOAMMR1 Planarcore Brush



Ordering Information

Part Number	Description
PVP1ARXR1	Planarcore AMAT™ Reflexion® PP-core, H ₂ O ₂
PVP1AMMR1	Planarcore AMAT Mirra Mesa® PP-core, H ₂ O ₂
PVP0ARXR1	Planarcore AMAT Reflexion PP-core, NH ₄ OH
PVP0AMMR1	Planarcore AMAT Mirra Mesa PP-core, NH ₄ OH

For More Information

Please call your Regional Customer Service Center today to learn what Entegris can do for you. Visit www.entegris.com and select the Customer Service link for the center nearest you.

Terms and Conditions of Sale

All purchases are subject to Entegris' Terms and Conditions of Sale. To view and print this information, visit www.entegris.com and select the Legal Notices link from the footer.

Entegris®, the Entegris Rings Design® and Planarcore® are registered trademarks of Entegris, Inc. Reflexion™, Mirra Mesa® and AMAT™ are trademarks of Applied Materials, Inc.

ENTEGRIS, INC.

Corporate Headquarters | 129 Concord Road | Billerica, MA 01821 USA
Customer Service Tel. +1 952 556 4181 | Customer Service Fax +1 952 556 8022
In North America 800 394 4083 | www.entegris.com